

2.4952/2.4631

Eine Nickel-Chrom-Legierung ähnlich wie Alloy 75, jedoch durch Aluminium- und Titanzusatz ausscheidungshärtbar. Die Legierung hat gute Korrosions- und Oxydationsbeständigkeit sowie hohe Zug- und Zeitstandfestigkeit bei Temperaturen bis 815°C. Verwendung für Gasturbinenteile (Schaufeln, Ringe und Scheiben), Schrauben, Rohrstützen in kerntechnischen Dampferzeugern, für Druckgusseinsätze und -kerne sowie Auslassventile in Verbrennungsmotoren.

A nickel-chromium alloy similar to alloy 75 but made precipitation hardenable by additions of aluminum and titanium. The alloy has good corrosion and oxidation resistance and high tensile and creep-rupture properties at temperatures to 1500°F (815°C). Used for gasturbine components (blades, rings, and discs), bolts, tube supports in nuclear steam generators, die-casting inserts and cores, and exhaust valves in internal-combustion engines.

Produktformen Product forms	Blech, Rundstab, Flachstab, Sechskant, Draht, Strangpressprofile, Schmiedematerial	Sheet, Round Bar, Flat Bar, Hexagon, Wire, Extruded Section, Forging Stock
Normen und Bezeichnungen Major Specifications	UNS N07080 BS 3076 (NA20), HR1, HR201, HR401, HR601 ASTM B 637 DIN 17742 W-Nr.: 2.4952, 2.4631 AECMA Pr EN 2188 - 2191, 2396, 2397	UNS N07080 BS 3076 (NA20), HR1, HR201, HR401, HR601 ASTM B 637 DIN 17742 W-Nr.: 2.4952, 2.4631 AECMA Pr EN 2188 - 2191, 2396, 2397
Thermische/ Physikalische Eigenschaften	Dichte, lb/in ³ 0.296 g/cm ³ 8.19 Schmelzbereich, °F 2410 - 2490 °C 1320 - 1365 Spezifische Wärme, Btu/lb•°F 0.107 J/kg•°C 448 Permeabilität bei 200 Oe (15.9 kA/m) 1.0006 Ausdehnungsbeiwert, 68 - 212°F 10-6 in/in•°F 7.1 20 - 100°C µm/m•°C 12.7 Wärmeleitfähigkeit, Btu • in/ft ² •h•°F 77.7 W/m•°C 11.2 Spez. elektr. Widerstand, ohm•circ mil/ft 746 µohm•m 1.24	Density, lb/in ³ 0.296 g/cm ³ 8.19 Melting Range, °F 2410 - 2490 °C 1320 - 1365 Specific Heat, Btu/lb•°F 0.107 J/kg•°C 448 Permeability at 200 Oersted (15.9 kA/m) 1.0006 Coefficient of Expansion, 68 - 212°F 10-6 in/in•°F 7.1 20 - 100°C µm/m•°C 12.7 Thermal Conductivity, Btu • in/ft ² •h•°F 77.7 W/m•°C 11.2 Electrical Resistivity, ohm•circ mil/ft 746 µohm•m 1.24
Mechanische Eigenschaften	(Ausscheidungsgehärtet)	(Precipitation Hardened)
Mechanical properties	Zeitstandfestigkeit (1000 Std) ksi MPa 1100°F / 595°C 94 650 1200°F / 650°C 73 500 1300°F / 705°C 51 350 1400°F / 760°C 32 220 1500°F / 815°C 16 110	Rupture Strength (1000 h) ksi MPa 1100°F / 595°C 94 650 1200°F / 650°C 73 500 1300°F / 705°C 51 350 1400°F / 760°C 32 220 1500°F / 815°C 16 110

Die Richtigkeit kann nicht garantiert werden.

The correctness cannot be guaranteed.